



TECHNOMATT PANEL

TEKNİK BİLGİ TABLOSU / TECHNICAL INFORMATIONS

TECHNICAL DATA SHEET			
No	FEATURE	RESULT	STANDARD
1	Gloss level (60° angle)	< 5 GLE	DIN 67530
2	Scratch resistance (rating group 4 B)	> 2 N	DIN 68861/T4
3	Assessment of surface resistance to wet heat (70°C)	No change (8B)	DIN 68861/T8
4	Assessment of surface resistance to dry heat (75°C)	No change (7D)	DIN 68861/T7
5	Colour Fastness (Delta E) (Colour difference after 200 h Xenon test)	DE <1,7	ISO 4892-2
6	Haze	<10	DIN 67530
7	Chemical resistance	No visible changes	DIN 68861/T1
8	Behaviour to water vapour	No changes visible	AMK
9	Thickness tolerance	± 0,3 mm	Gizir
10	Bow tolerance	3,5 mm / m	Gizir
11	Density	≥ 1,07 ≤ 1,12 g/cm ³	ISO 1183-1
12	Resistance to steel wool	class 1. no changes or scratches visible	TEST METHOD QPA-25-LT

- (*) Sonuçlar, yapılan testlerin ortalama ağırlıkları alınarak belirlenmiştir. / (*) These values are weighted average of the test results.